



Version 1

INTÉRIEUR

# AQUASTRIA VELOURS

Waterborne interior acrylic paint - Velvet





#### PRODUCT OVERVIEW

New and maintenance work for interior walls in dry rooms Commercial and residential sites

#### BENEFITS

High hiding power No yellowing (even in dark rooms) Wet scrub resistance (class 2 according to NF EN 13300) Quick drying Washable

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

# **TECHNICAL SPECIFICATIONS**

Finish Density Solids by VOC (directive 2004/42/CE)	<ul> <li>silky satin smooth</li> <li>1.37 +/- 0,05 Kg/l</li> <li>Weight: 60 +/- 2% Volume: 43 +/- 2%</li> <li>EU limit value for this product . (cat. A/a): 30 g/l (2010). This product contains max 15 g/lVOC</li> </ul>	
Flash point	: Not applicable	
Gloss level at to 85°	: 10 - 15 %	
Practical coverage	: 9 to 10 m <sup>2</sup> /l per coat depending on surface texture.	
Drying time (20°C -65% RH)	: Dry : 2 h	
	Recoat : 6 h	
Colours	: White, medium and deep tints from the Peintures	
	Maestria colour chart	
Storage	: Can be kept for 1 year in unopened original container.	
	Protect from freezing and high temperatures.	







Version 1



# AQUASTRIA VELOURS

Waterborne interior acrylic paint - Velvet

# SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM. These recommendations do not override a specific description of the substrate.

# APPLICATION

Application conditions Application equipment	<ul><li>DTU 59.1</li><li>Brush, Roller, Enamel roller. Airless spray-gun.</li></ul>
Clean-up solvent	: Water
Thinner	: Water
Dilution	: Brush (Ready to use), Roller (Ready to use), Enamel roller (5 to 10 %). Airless spray-gun (15 to 20 %).

### SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
hydraulic binder-baser coatings,	Apply 1 coat of PRIM O 2010	Apply 2 coats of AQUASTRIA VELOURS
plasterboard, previously painted		
surfaces in good conditions		
plaster	Apply 1 coat of IKARPRIM	

#### CONTAINER SIZE

1L - 2.5L - 5L - 15L

#### SAFETY MEASURES

Refer to the Safety Data Sheet



Laboratoire Recherche & Développement - Usine - Administration Z.I. -1, rue Denis Papin - 09100 PAMIERS - Tél. 05 61 67 97 40 - Fax : 05 61 67 05 47 Contact : accueil@maestria.fr - Site internet : www.maestria.fr



Page 2/2

This description sheet is designed to inform customers about the properties of our product. The information is based on our current knowledge. However, this information cannot replace an appropriate description of the nature and condition of the base to be painted. Techniques and technology are constantly developing and it is up to our customers, before using any product, to check with our departments that the sheet has not been updated and replaced by a more recent version. The present description sheet replaces any previous sheet about the same product. The above technical data does not engender acceptance of any guarantee