

BANDAX ENDUIT TEINTES

Cold plastic coating for urban and road marking



Classement AFNOR NFT 36 005 Famille I Classe 4a

DESCRIPTION

Long-lasting, two component, road and urban colour cold plastic coating and based on certified paint formulas. A range of tints designed to satisfy all colour urban marking needs.

DESTINATION

Road and urban marking

FONCTIONAL LIFESPAN

Dose : 2000-3000 g/m², depending on the sand-depht. of the surface.
Drying : 10 min at 20°C.

PROPERTIES

BANDAX ENDUIT TEINTES:- enables to make colour markings (parking lots, sports fields, etc...) on hydrocarbon or concrete surfaces.- its drying time is less than 10 minutes for a dosage of 3000 g/m² at 20°C.

TECHNICAL FEATURES

Density : 2.2 g/cm³ depending on the tin
Storage : 6 months in its unaltered and sealed original container.
Paint thinner : Thinner 258
Clean-up solvent : Thinner EST
Pot life (at 20°C) : 10 min.

BANDAX ENDUIT TEINTES

Cold plastic coating for urban and road marking

APPLICATION

SURFACE PREPARATION

HYDROCARBON

The coated surface must be at least one month old prior to application. If it is younger, please contact our laboratory.

CONCRETE

In compliance with recommendation set forth in DTU 59-3 concerning the preparation and quality of flooring before painting operations: dry surface, clean, free from any form of pollutant, no rising damp and showing sufficient roughness to enable the coating to adhere. The concrete surface must be at least three weeks old prior to application. For coating over concrete, a first layer of PRIMAIRE TOLEDO is to be applied with a dosage of 300-400 g/m². After drying, a second layer of BANDAX ENDUIT TEINTES should be applied with a dosage included between 2-3 kg/m², depending on the surface

CONDITION OF APPLICATION

Surface temperature: Between 5°C and 40°C and at least 3°C higher than the dew point in order to eliminate any risk of condensation. Atmospheric conditions: The temperature must be between 10°C and 40°C. The humidity must be between 0% and 85%.

EQUIPMENT AND DILUTION FOR APPLICATION

Palette knife

Dilution: Diluting agent 258
Use the smooth or toothed spatula.

PRODUCT PREPARATION

BANDAX ENDUIT TEINTES is a two-component cold plastic coating. The base coat and the powder bag of hardener must therefore be mixed. The pot life is about 5 minutes at 20°C.

CLEANING

Cleaning equipment with EST diluting agent.

PACKAGING

Available tints : traffic green, yellow, blue, Ral 5015, red, black, all special tints included in the RAL colour model, upon request: 6 kg kit (base coat + 1 powder bag of hardener).