




# DECONATURE VELOURS

Waterborne interior acrylic paint - Velvet



## PRODUCT OVERVIEW

New and maintenance work  
Excellent top coat for interior walls in dry rooms  
Ideal for HQE, LEED or BREEAM® projects

## BENEFITS

Odourless  
Excellent covering  
No yellowing  
Quick drying  
Washable  
Certified EUROPEAN ECOLABEL  
Complies with LEED and BREEAM® tests  
Good wet scrub resistance (Class 2 according to NF EN 13300)

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

## TECHNICAL SPECIFICATIONS

<b>Density</b>	: 1.46 +/- 0,05 Kg/l
<b>Solids by</b>	: Weight: 67 +/- 2%                      Volume: 50 +/- 2%
<b>VOC (directive 2004/42/CE)</b>	: EU limit value for this product . (cat. A/a): 30 g/l (2010). This product contains max 1 g/IVOC
<b>Flash point</b>	: Not applicable
<b>Gloss level at to 85°</b>	: 15%
<b>Practical coverage</b>	: 9 to 11 m <sup>2</sup> /l per coat depending on surface texture.
<b>Drying time (20°C -65% RH)</b>	: Dry                      : 2 h Recoat                : 8 h
<b>Colours</b>	: White, medium and deep tints from the Peintures Maestria colour chart
<b>Storage</b>	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.



## DECONATURE VELOURS

Waterborne interior acrylic paint - Velvet

### SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

Must be applied on coherent and porous substrates.

Unpainted surfaces must be previously primed.

Lime based coating must be removed with an appropriate cleaner and then rinsed with water.

These recommendations do not override a specific description of the substrate.

### APPLICATION

- Application conditions** : DTU 59.1
- Application equipment** : Brush, Roller, Airless spray-gun.
- Clean-up solvent** : Water
- Thinner** : Water
- Dilution** : Brush (Ready to use), Roller (Ready to use), Airless spray-gun (5 to 10 %).

### SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
plaster	Apply 1 coat of Ikarprim	Apply 2 coats of DECONATURE VELOURS
plasterboard, cement, previously painted surfaces in good condition	Apply 1 coat of PRIM 0 2010	

### CONTAINER SIZE

2.5L - 15L

### SAFETY MEASURES

Refer to the Safety Data Sheet