

# FLEXIKAR TALOCHE SILOXANE GM

Waterborne exterior elastomeric trowelled coating - Medium grain



## PRODUCT OVERVIEW

New and maintenance work  
Residential and commercial sites  
Recommended for a wide variety of exterior masonry projects  
Ideal for vertical walls with cracks (from 0 to 2.0 mm) and small irregularities

## BENEFITS

Excellent crack resistance (from 0 to 2.0 mm)  
Good adhesion  
Microporous  
Grain size 1.5 mm  
French classification A2 to A5 - Standard P84.403  
European classification G3E4S1V2W2A2C0 to G3E5S1V2W2A5C0 - Standard EN 1062-1

AFNOR Classification NFT 36 005 Rating Family II Class 2b/1b

## TECHNICAL SPECIFICATIONS

<b>Density</b>	: 1.64 +/- 0,05 Kg/l
<b>Solids by</b>	: Weight: 82+/- 2%
<b>Flash point</b>	: Not applicable
<b>Drying time (20°C -65% RH)</b>	: Dry : 6 h Recoat : 12 h
<b>Colours</b>	: White and pastel tints from the Peintures Maestria colour chart
<b>Storage</b>	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.

## FLEXIKAR TALOCHE SILOXANE GM

Waterborne exterior elastomeric trowelled coating - Medium grain



### SURFACE PREPARATION

As stated by DTU 42.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR BACTERICIDE.

If required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR BACTERICIDE.

Unpainted surfaces must be primed with a suitable primer.

These recommendations do not override a specific description of the substrate.

### APPLICATION

<b>Application conditions</b>	: DTU 42.1
<b>Application equipment</b>	: Stainless steel float.
<b>Clean-up solvent</b>	: Water
<b>Dilution</b>	: Stainless steel float (Ready to use).

### SYSTEM RECOMMENDATIONS

system:	A2:	A3:	A4:	A5:	A4 "inverted":
first coat	2000 g/m <sup>2</sup> of undiluted FLEXIKAR TALOCHE	250 g/m <sup>2</sup> of FLEXIKAR INTER diluted to 10%	400 g/m <sup>2</sup> of undiluted FLEXIKAR INTER	400 g/m <sup>2</sup> of undiluted FLEXIKAR INTER + mesh + 400 g/m <sup>2</sup> of undiluted FLEXIKAR INTER	2000 g/m <sup>2</sup> of undiluted FLEXIKAR TALOCHE
second coat		2000 g/m <sup>2</sup> of undiluted FLEXIKAR TALOCHE	2000 g/m <sup>2</sup> of undiluted FLEXIKAR TALOCHE	2000 g/m <sup>2</sup> of undiluted FLEXIKAR TALOCHE	500 g/m <sup>2</sup> of undiluted MONOFLEX SILOXANE
elongation resistance	0-0.2 mm	0.2-0.5 mm	0.5-1 mm	1-2 mm	0.5-1 mm

NOTE: Consumption of FLEXIKAR TALOCHE can vary depending on the substrate. A reference surface must be achieved in order to know the exact consumption.

### CONTAINER SIZE

25Kg

### SAFETY MEASURES

Refer to the Safety Data Sheet