

IKARFIX IP

Waterborne interior & exterior acrylic primer



PRODUCT OVERVIEW

Residential and commercial sites
Specially recommended after chemical pickling

BENEFITS

Excellent adhesion (despite the presence of paraffin residuals)
Great hiding power
Microporous

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

TECHNICAL SPECIFICATIONS

Finish	: flat
Density	: 1.44 +/- 0,05 Kg/l
Solids by	: Weight: 64 +/- 2% Volume: 48 +/- 2%
VOC (directive 2004/42/CE)	: EU limit value for this product . (cat. A/h): 30 g/l (2010). This product contains max 30 g/lVOC
Flash point	: Not applicable
Gloss level at to 60°	: < 10%
Practical coverage	: 150 to 200 gr/m ² per coat depending on surface texture.
Drying time (20°C -65% RH)	: Dry : 1 h Recoat : 12 h
Colours	: White
Storage	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.

IKARFIX IP

Waterborne interior & exterior acrylic primer



SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Interior: Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR BACTERICIDE.

Exterior: if required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR BACTERICIDE.

These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions	: DTU 59.1
Application equipment	: Brush, Facade roller.
Clean-up solvent	: Water
Thinner	: Water
Dilution	: Brush (0 to 5 %), Facade roller (0 to 5 %).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
concrete, cement, hydraulic binder-based coating, previously painted surfaces in good condition	Apply 1 coat of IKARFIX IP	Apply 1 or 2 coats of interior or exterior paints

CONTAINER SIZE

20 Kg

SAFETY MEASURES

Refer to the Safety Data Sheet