

# KATEX

Waterborne interior & exterior acrylic paint



## PRODUCT OVERVIEW

New and maintenance work  
Ideal for large surfaces in good condition  
Interior: only dry rooms

## BENEFITS

High hiding power  
Good adhesion  
Good alkali resistance  
Microporous  
Wet scrub resistance (Class 3 according to NF EN 13300)

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

## TECHNICAL SPECIFICATIONS

<b>Finish</b>	: flat
<b>Density</b>	: 1.65 +/- 0,05 Kg/l
<b>Solids by</b>	: Weight: 66 +/- 2%                      Volume: 44 +/- 2%
<b>VOC (directive 2004/42/CE)</b>	: EU limit value for this product (cat. A/a): 75 g/l (2007), (cat. A/a): 30 g/l (2010). This product contains max 30 g/IVOC
<b>Flash point</b>	: Not applicable
<b>Gloss level at to 60°</b>	: < 5 %
<b>Practical coverage</b>	: 5 to 10 m <sup>2</sup> /l per coat depending on surface texture.
<b>Drying time (20°C -65% RH)</b>	: Dry                      : 1 h Recoat                : 2 h
<b>Colours</b>	: White and pastel tints from the Peintures Maestria colour chart
<b>Storage</b>	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.



## KATEX

Waterborne interior & exterior acrylic paint

### SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Interior: Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM.

Exterior: if required an high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR AM.

These recommendations do not override a specific description of the substrate.

### APPLICATION

<b>Application conditions</b>	: DTU 59.1
<b>Application equipment</b>	: Brush, Roller, Facade roller, Airless spray-gun.
<b>Clean-up solvent</b>	: Water
<b>Thinner</b>	: Water
<b>Dilution</b>	: Brush (0 to 5 %), Roller (0 to 5 %), Facade roller (0 to 5 %), Airless spray-gun (0 to 5 %).

### SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
exterior: concrete, hydraulic binder-based coating	Apply 1 coat of IKARFIX S or IKARFIX O or IKARFIX IP	Apply 2 coats of KATEX
interior: concrete, hydraulic binder-based coating, previously painted surfaces in good condition	Apply 1 coat of IMPRESSION PLACO or PRIM O 2010 or AQUASTRIA PRIMER	
interior: previously painted weatherboarding, old galvanised weatherboarding	Apply 1 coat of a suitable primer	
plaster	Apply 1 coat of IKARPRIM	

### CONTAINER SIZE

2.5L - 15L

### SAFETY MEASURES

Refer to the Safety Data Sheet