

VERNIKAR

Solventborne interior & exterior wood varnish



PRODUCT OVERVIEW

Interior : VERNIKAR MAT (flat)
Interior & exterior : VERNIKAR SATIN, VERNIKAR BRILLANT (high gloss) and VERNIKAR MARIN

BENEFITS

VERNIKAR MAT :

- Flat alkyd-urethane varnish
- Excellent levelling

VERNIKAR SATIN :

- Satin alkyd-urethane varnish
- Excellent levelling

VERNIKAR BRILLANT :

- Gloss alkyd-urethane varnish
- High gloss and excellent levelling

VERNIKAR MARIN :

- Very high-gloss marine varnish
- Excellent durability in marine atmosphere

AFNOR Classification NFT 36 005 Rating Family I Class 4a

TECHNICAL SPECIFICATIONS

VOC (directive 2004/42/CE)	: EU limit value for this product . (cat. A/e): 400 g/l (2010). This product contains max 400 g/IVOC
Flash point	: 23°C to 55°C
Practical coverage	: 10 to 15 m ² /l per coat depending on surface texture.
Drying time (20°C -65% RH)	: Dry : 4 to 5 h Recoat : 24 h
Colours	: Colourless
Storage	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.



VERNIKAR

Solventborne interior & exterior wood varnish

SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

For maintenance work, remove peeling paint by brushing, scraping or sanding. Old glossy painted surfaces must be sanded or washed with an appropriate cleaner and then rinsed with water.

If necessary, substrates must first be treated with a fungal treatment.

These recommendations do not override a specific description of the substrate.

APPLICATION

- Application conditions** : DTU 59.1
Application equipment : Brush.
Clean-up solvent : White spirit
Thinner : White spirit
Dilution : Brush (Ready to use).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
wood	Apply 1 coat of VERNIKAR diluted to 5%	Apply 2 coats of VERNIKAR

CONTAINER SIZE

1L - 5L

SAFETY MEASURES

Refer to the Safety Data Sheet