


# AQUAPORE

Microporous acrylic paint for interior and exterior wood joinery



## PRODUCT OVERVIEW

New and maintenance work for interior and exterior wood joinery  
Can be used as primer and top coat

## TECHNICAL SPECIFICATIONS

FINISH	satin
DENSITY	1.27 +/- 0,05 Kg/l
SOLIDS BY	Weight : 54 +/- 2% Volume : 42 +/- 2%
VOC	EU limit value for this product (cat. A/d): 150 g/l (2007), (cat. A/d): 130 g/l (2010). <b>This product contains max 75 g/l VOC</b>
GLOSS LEVEL AT	35 +/- 5 % 60°
AFNOR CLASSIFICATION NFT 36 005	Rating Family I Class 7b2
COLOURS	White, medium and deep tints from the Peintures Maestria colour chart
CONTAINER SIZE	0.5L - 2.5L - 10L

## SURFACE PREPARATION | APPLICATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Previous peeling paints must be removed. Previously painted surfaces in good condition must be sanded or washed with an appropriate cleaner and then rinsed well.

A cross-cut test must be performed to ensure compatibility of AQUAPORE with the previous coats kept on the substrate.

Do not apply in the event of exudation of resin or sap.

Staining woods with a risk of tannin migration such as redwood or cedar must be primed with a suitable primer. Metal surfaces should be properly prepared and primed using FERROSOTER PRIMAIRE. These recommendations do not override a specific description of the substrate.

<b>Application conditions</b>	DTU 59.1
<b>Application equipment</b>	Brush : Dilution 0 to 10 % Roller : Dilution 2 to 5 %.
<b>Practical coverage</b>	10 to 14 m <sup>2</sup> /l per coat depending on surface texture.
<b>Thinner / Clean-up solvent</b>	Water
<b>Drying time (20°C -65% RH)</b>	Dry : 3 h Recoat : 8 h

# AQUAPORE

## SYSTEM RECOMMENDATIONS

Substrate	wood joinery without a risk of tannin staining	unpainted interior wood joinery with a risk of tannin staining	unpainted exterior wood joinery with a risk of tannin staining
Primer coat	Apply 1 coat of AQUAPORE diluted to 10% using a brush	Apply 1 coat of NORWAY	Apply 1 coat of IKARPRIM
Top coat	Interior: Apply 1 or 2 coats of AQUAPORE diluted to 5% Exterior: Apply 2 coats of AQUAPORE diluted to 5% (apply an additional coat on the water jets)		

## SAFETY MEASURES

<b>Storage</b>	Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.
<b>Précaution d emploi</b>	Shake or stir before use. Use in well-ventilated areas. Keep out of reach of children. For personal protection, refer to the Safety Data Sheet (SDS).
<b>Transport</b>	Not subject to ADR regulations (European Agreement concerning the International Carriage of Dangerous Goods by Road).
<b>Gestion des déchets</b>	Close the container tightly after use. Do not dispose of residues in the sewer or with household waste. Please take your empty container to an approved collection center. Contact local authorities for information on disposal and collection procedures.