

AQUASTRIA PRIMER

Waterborne interior alkyd primer



PRODUCT OVERVIEW

Universal primer for a wide variety of substrates
Ideal for achieving a perfect finish

BENEFITS

Excellent adhesion
High hiding power
Microporous
Odourless

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

TECHNICAL SPECIFICATIONS

Finish	: flat
Density	: 1.49 +/- 0,05 Kg/l
Solids by	: Weight: 60 +/- 2% Volume: 40 +/- 2%
VOC (directive 2004/42/CE)	: EU limit value for this product . (cat. A/g): 30 g/l (2010). This product contains max 30 g/IVOC
Flash point	: Not applicable
Gloss level at to 60°	: < 10%
Practical coverage	: 8 to 10 m ² /l per coat depending on surface texture.
Drying time (20°C -65% RH)	: Dry : 1 to 2 h Recoat : 6 h
Colours	: White
Storage	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.



AQUASTRIA PRIMER
Waterborne interior alkyd primer

SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.
For maintenance work, remove peeling paint by brushing, scraping or sanding. Old glossy painted surfaces must be sanded or washed with an appropriate cleaner and then rinsed with water.
In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM. These recommendations do not override a specific description of the substrate.

APPLICATION

- Application conditions** : DTU 59.1
- Application equipment** : Brush, Roller.
- Clean-up solvent** : Water
- Thinner** : Water
- Dilution** : Brush (Ready to use), Roller (Ready to use).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
wood and wood joinery, hydraulic binder-based coating, plasterboard	Apply 1 coat of AQUASTRIA PRIMER	Apply 1 or 2 coats of waterborne alkyd or acrylic paint
plaster	Apply 1 coat of IKARPRIM	

CONTAINER SIZE

5L - 15L

SAFETY MEASURES

Refer to the Safety Data Sheet