

# CUIRAS 400

Waterborne exterior elastomeric coating



## PRODUCT OVERVIEW

New and maintenance work  
Residential and commercial sites  
Recommended for a wide variety of exterior masonry projects

## BENEFITS

Good adhesion  
Microporous  
Great dirt pick-up resistance  
French classification A1 - Standard P84.403  
European classification G3E4S1V2W2A1C0

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

## TECHNICAL SPECIFICATIONS

<b>Finish</b>	: flat
<b>Density</b>	: 1.55 +/- 0,05 Kg/l
<b>Solids by</b>	: Weight: 72 +/- 2%
<b>VOC (directive 2004/42/CE)</b>	: EU limit value for this product . (cat. A/c): 40 g/l (2010). This product contains max 40 g/IVOC
<b>Flash point</b>	: Not applicable
<b>Gloss level at to 85°</b>	: < 3%
<b>Practical coverage</b>	: 350 to 500 gr/m <sup>2</sup> per coat depending on surface texture.
<b>Drying time (20°C -65% RH)</b>	: Dry : 4 h Recoat : 12 h
<b>Colours</b>	: White and pastel tints from the Peintures Maestria colour chart
<b>Storage</b>	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.

## CUIRAS 400

Waterborne exterior elastomeric coating



### SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named for façade.

If required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR AM.

Unpainted surfaces must be primed with a suitable primer.

These recommendations do not override a specific description of the substrate.

### APPLICATION

<b>Application conditions</b>	: DTU en vigueur.
<b>Application equipment</b>	: Brush, Facade roller. Airless spray-gun.
<b>Clean-up solvent</b>	: Water
<b>Thinner</b>	: Water
<b>Dilution</b>	: Brush (0 to 3 %), Facade roller (0 to 3 %). Airless spray-gun (0 to 3 %).

### SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
concrete, cement, hydraulic binder-based coating, previously painted surfaces in good condition	Apply 1 coat of IKARFIX S or IKARFIX O	Apply 1 or 2 coats of CUIRAS 400 depending on the substrate
stripped surfaces	Apply 1 coat of IKARFIX IP	

### CONTAINER SIZE

15L

### SAFETY MEASURES

Refer to the Safety Data Sheet