

# DECOPUR VELOURS

Waterborne depolluting paint - Velvet



## PRODUCT OVERVIEW

New and maintenance work  
Residential and commercial sites  
Top coat for interior walls in dry rooms  
Ideal for schools, retirement homes, nurseries...

## BENEFITS

Odourless  
Quick drying  
Depolluting by elimination of formaldehyde molecules  
Excellent wet scrub resistance (Class 1 according to NF EN 13300)  
Certified European Ecolabel (VOC < 1 g/l)  
No yellowing (even in the dark)

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

## TECHNICAL SPECIFICATIONS

<b>Density</b>	: 1.44 +/- 0,05 Kg/l	
<b>Solids by</b>	: Weight: 60 +/- 2%	Volume: 42 +/- 2%
<b>VOC (directive 2004/42/CE)</b>	: EU limit value for this product . (cat. A/a): 30 g/l (2010). This product contains max 1 g/IVOC	
<b>Gloss level at to 60°</b>	: 10 +/- 5 %	
<b>Practical coverage</b>	: 9 to 11 m²/l per coat depending on surface texture.	
<b>Drying time (20°C -65% RH)</b>	: Dry : 2 h Recoat : 8 h	
<b>Colours</b>	: White, medium and deep tints from the Peintures Maestria colour chart	
<b>Storage</b>	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.	

## DECOPUR VELOURS

Waterborne depolluting paint - Velvet



### SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

Must be applied on coherent and porous substrates.

Unpainted surfaces must be previously primed.

These recommendations do not override a specific description of the substrate.

### APPLICATION

<b>Application conditions</b>	: DTU 59.1
<b>Application equipment</b>	: Brush, Roller, Airless spray-gun.
<b>Clean-up solvent</b>	: Water
<b>Thinner</b>	: Water
<b>Dilution</b>	: Brush (Ready to use), Roller (Ready to use), Airless spray-gun (0 to 5 %).

### SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
plaster	Apply 1 coat of IKARPRIM	Apply 2 coats of DECOPUR VELOURS
concrete, plasterboard, cement, hydraulic binder-based coating, previously painted surfaces in good condition	Apply 1 coat of PRIM O 2010 or AQUASTRIA PRIMER or DECONATURE IMPRESSION	

### CONTAINER SIZE

5L, 15L

### SAFETY MEASURES

Refer to the Safety Data Sheet