

DECOSILANE

Waterborne ceiling paint - Flat



PRODUCT OVERVIEW

Paint for ceilings in dry rooms
Low VOC content
Ideal for commercial and institutional sites such as hospitals, nursing homes, schools

BENEFITS

Odourless
Very low VOC content (< 1 g/l)
Great hiding of minor surface imperfections
Wet scrub resistance (Class 3 according to NF EN 13300)

AFNOR Classification NFT 36 005 Rating Family I Class 7b2/10c

TECHNICAL SPECIFICATIONS

Finish	: flat
Density	: 1.48 +/- 0,05 Kg/l
Solids by	: Weight: 57 +/- 2% Volume: 37 +/- 2%
VOC (directive 2004/42/CE)	: EU limit value for this product . (cat. A/a): 30 g/l (2010). This product contains max 1 g/IVOC
Flash point	: Not applicable
Gloss level at to 85°	: < 1.5%
Practical coverage	: 10 to 14 m ² /l per coat depending on surface texture.
Drying time (20°C -65% RH)	: Dry : 1 h Recoat : 4 to 6 h
Colours	: White
Storage	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.



DECOSILANE

Waterborne ceiling paint - Flat

SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

Unpainted surfaces must be previously primed.

These recommendations do not override a specific description of the substrate.

APPLICATION

- Application conditions** : DTU 59.1
Application equipment : Brush, Roller, Airless spray-gun.
Clean-up solvent : Water
Thinner : Water
Dilution : Brush (0 to 5 %), Roller (0 to 5 %), Airless spray-gun (10 to 15 %).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
plaster	Apply 1 coat of IKARPRIM	Apply 1 or 2 coats of DECOSILANE depending on the substrate
concrete, hydraulic binder-based coating, fibre cement, plasterboard	Apply 1 coat of PRIM 0 2010	
previously painted surfaces in good condition		

CONTAINER SIZE

5L - 15L

SAFETY MEASURES

Refer to the Safety Data Sheet