

FLEXIKAR INTER

Waterborne exterior elastomeric coating



PRODUCT OVERVIEW

New and maintenance work
Residential and commercial sites
Recommended for a wide variety of exterior masonry projects
Ideal for vertical walls with cracks (from 0 to 2.0 mm)

BENEFITS

Excellent crack resistance (from 0 to 2.0 mm)
Good adhesion
Microporous
French classification A2 to A5 - Standard P84.403
European classification G3E4S1V2W2A2C0 to G3E5S1V2W2A5C0 - Standard EN 1062-1

AFNOR Classification NFT 36 005 Rating Family II Class 2b/1b

TECHNICAL SPECIFICATIONS

Density	: 1.28 +/- 0,05 Kg/l
Solids by	: Weight: 63 +/- 2%
Practical coverage	: 250 to 800 gr/m ² per coat depending on surface texture.
Drying time (20°C -65% RH)	: Dry : 12 h Recoat : 24 h
Colours	: White
Storage	: Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.

FLEXIKAR INTER

Waterborne exterior elastomeric coating



SURFACE PREPARATION

As stated by DTU 42.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR BACTERICIDE.

If required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR BACTERICIDE.

Unpainted surfaces must be primed with a suitable primer.

These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions	: DTU 42.1
Application equipment	: Facade roller.
Clean-up solvent	: Water
Thinner	: Water
Dilution	: Facade roller (Ready to use).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
concrete, cement, hydraulic binder-based coating	Apply 1 coat of IKARFIX O or IKARFIX S or IKARFIX IP	Apply 1 coat of FLEXIKAR INTER NOTE: refer to Technical Data Sheet of FLEXIKAR TALOCHE for the consumption
plaster, lime based coating	Apply 1 coat of IKARFIX S	
previously painted surfaces in good condition	Apply 1 coat of IKARFIX O	
stripped surfaces	Apply 1 coat of IKARFIX IP	

CONTAINER SIZE

15L

SAFETY MEASURES

Refer to the Safety Data Sheet