IKARFIX O

Waterborne interior & exterior acrylic paint

EXTÉRIEUR

EAU | INT | EXT | EXT INT

PRODUCT OVERVIEW

New and maintenance work
Commercial and residential sites in dry and wet rooms

BENEFITS

Excellent adhesion
Good alkali resistance
Great hiding power
Microporous

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

TECHNICAL SPECIFICATIONS

Density	**:** 1.54 +/- 0,05 Kg/l
Solids by	**:** Weight: 68 +/- 2% Volume: 50 +/- 2%
VOC (directive 2004/42/CE)	**:** EU limit value for this product . (cat. A/h): 30 g/l (2010). This product contains max 30 g/lVOC
Flash point	**:** Not applicable
Practical coverage	**:** 150 to 200 gr/m² per coat depending on surface texture.
Drying time (20°C -65% RH)	**:** Dry : 1 h Recoat : 12 h
Colours	**:** White
Storage	**:** Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures.

IKARFIX O
Waterborne interior & exterior acrylic paint

EXTÉRIEUR

SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.
Interior: Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.
In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM.
Exterior: if required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR AM.
For powdery surface, apply 1 coat of IKARFIX S.
These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions	:	DTU 59.1
Application equipment	:	Brush, Facade roller.
Clean-up solvent	:	Water
Thinner	:	Water
Dilution	:	Brush (Ready to use), Facade roller (Ready to use).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
concrete, cement, hydraulic binder-based coating	Apply 1 coat of IKARFIX O	Apply 1 or 2 coats of interior or exterior paints

CONTAINER SIZE

7Kg / 20Kg

SAFETY MEASURES

Refer to the Safety Data Sheet