



IKARFIX S

Solventborne exterior acrylic primer









PRODUCT OVERVIEW

Residential and commercial sites Ideal for slightly brittle surface or after a high pressure cleaning

BENEFITS

Excellent adhesion High alkali resistance Microporous Ideal for powdery surface

AFNOR Classification NFT 36 005 Rating Family I Class 7b1

TECHNICAL SPECIFICATIONS

Finish : flat

Density : 1.37 +/- 0,05 Kg/l

Solids by : Weight: 66 +/- 2% Volume: 39 +/- 2% VOC (directive 2004/42/CE) : EU limit value for this product (cat. A/h): 750 g/l

(2007),. (cat. A/h): 750 g/l (2010). This product contains max 500 g/IVOC

Flash point : 23°C to 55°C

Practical coverage : 150 to 200 gr/m² per coat depending on surface

texture.

Drying time (20°C -65% RH) : Dry : 4 h

Recoat : 6 h

Colours : White

Storage : Can be kept for 1 year in unopened original container.

Protect from freezing and high temperatures.







IKARFIX S Solventborne exterior acrylic primer



SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM. If required a high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR AM.

These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions : DTU 59.1

Application equipment : Brush, Facade roller.

Clean-up solvent : White spirit
Thinner : White spirit

Dilution : Brush (Ready to use), Facade roller (0 to 5 %).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
concrete, cement, hydraulic	Apply 1 coat of IKARFIX S	Apply 1 or 2 coats of exterior paint
binder-based coating, previously		
painted surfaces in good condition		

CONTAINER SIZE

15L - 2.5L

SAFETY MEASURES

Refer to the Safety Data Sheet



