



IKARSOIE

Solventborne interior alkyd urethane paint - Satin













PRODUCT OVERVIEW

New and maintenance work Ideal for use on interior wood and wood joinery

BENEFITS

High hiding power Fast drying Washable

AFNOR Classification NFT 36 005 Rating Family I Class 4a

TECHNICAL SPECIFICATIONS

Finish : satin

Density : 1.29 +/- 0,05 Kg/l
Solids by : Weight: 70 +/- 2% Volume: 53 +/- 2%
VOC (directive 2004/42/CE) : EU limit value for this product (cat. A/d): 400 g/l

(2007),. (cat. A/d): 300 g/l (2010). This product contains max 300 g/IVOC

Flash point : 23° C to 55° C Gloss level at to 60° : $20 \pm 5\%$

Practical coverage : 10 to 12 m²/l per coat depending on surface texture.

Drying time (20°C -65% RH) : Dry : 8 to 10 h Recoat : 24 h

Colours : White, medium and deep tints from the Peintures

Maestria colour chart

Storage : Can be kept for 1 year in unopened original container.

Protect from freezing and high temperatures.











Solventborne interior alkyd urethane paint - Satin



SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

For maintenance work, remove peeling paint by brushing, scraping or sanding. Old glossy painted surfaces must be sanded or washed with an appropriate cleaner and then rinsed with water.

These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions : DTU 59.1

Application equipment : Brush, Roller, Airless spray-gun.

Clean-up solvent : White spirit
Thinner : White spirit

Dilution : Brush (Ready to use), Roller (Ready to use), Airless spray-gun (Ready to use).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
wood and wood joinery	Apply 1 coat of IKARPRIM	Apply 2 coats of IKARSOIE
previously painted surfaces in good		
condition		
pretreated galvanised metal	Apply 1 coat of GALVASOTER	
	PRIMAIRE	
ferrous metals	Apply 1 coat of FERROSOTER]
	PRIMAIRE	

CONTAINER SIZE

0.5L - 2.5L - 10L

SAFETY MEASURES

Refer to the Safety Data Sheet



