



IMPRESSION PLACO

Waterborne interior acrylic primer













PRODUCT OVERVIEW

New and maintenance work Primer for low porosity surfaces in good condition Ideal for HQE projects

BENEFITS

Odourless High hiding power Good adhesion Great sealing properties Certified EUROPEAN ECOLABEL

AFNOR Classification NFT 36 005 Rating Family I Class 7b2

TECHNICAL SPECIFICATIONS

Finish : flat

Density : 1.67 +/- 0.05 Kg/l

Solids by : Weight: 68 +/- 2% Volume: 47 +/- 2% VOC (directive 2004/42/CE) : EU limit value for this product . (cat. A/g): 30 g/l (2010).

This product contains max 10 g/IVOC

Flash point : Not applicable

Gloss level at to 60° : < 10 %

Practical coverage : 5 to 10 m²/l per coat depending on surface texture.

Drying time (20°C -65% RH) : Dry : 1 h

2 h Recoat

Colours : White

Storage : Can be kept for 1 year in unopened original container.

Protect from freezing and high temperatures.







IMPRESSION PLACO Waterborne interior acrylic primer



SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

For maintenance work, remove peeling paint by brushing, scraping or sanding. Old glossy painted surfaces must be sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR BACTERICIDE.

These recommendations do not override a specific description of the substrate.

APPLICATION

Application conditions : DTU 59.1

Application equipment : Brush, Roller, Airless spray-gun.

Clean-up solvent : Water
Thinner : Water

Dilution : Brush (5 to 10 %), Roller (5 to 10 %), Airless spray-gun (5 to 10 %).

SYSTEM RECOMMENDATIONS

Substrate	Primer coat	Top coat
plasterboard, concrete, hydraulic	Apply 1 coat of IMPRESSION PLACO	Apply 1 or 2 coats of waterborne alkyd or acrylic paint
binder-based coating, unstained		
surfaces in good condition		
stained surfaces	Apply 1 coat of NORWAY or	
	IKARPRIM	
plaster	Apply 1 coat of IKARPRIM	

CONTAINER SIZE

15L

SAFETY MEASURES

Refer to the Safety Data Sheet



