

PRESTOLITE

Solventborne exterior PLIOLITE® based paint



PRODUCT OVERVIEW

New and maintenance work
Residential and commercial sites
Recommended for marine and industrial environments

BENEFITS

High alkali and acid resistance
Excellent adhesion
Microporous
French classification D2 - Standard P84.403
European classification G3E3S1V2W1A0C0 - Standard EN 1062-1

AFNOR Classification NFT 36 005 Rating Family I Class 7b1

TECHNICAL SPECIFICATIONS

| | |
|-----------------------------------|--|
| Finish | : flat |
| Density | : 1.56 +/- 0,05 Kg/l |
| Solids by | : Weight: 73 +/- 2% Volume: 50 +/- 2% |
| VOC (directive 2004/42/CE) | : EU limit value for this product . (cat. A/c): 430 g/l (2010). This product contains max 430 g/IVOC |
| Flash point | : 23°C to 55°C |
| Gloss level at to 85° | : < 5 % |
| Practical coverage | : 6 to 12 m²/l per coat depending on surface texture. |
| Drying time (20°C -65% RH) | : Dry : 10 h Recoat : 24 h |
| Colours | : White and pastel tints from the Peintures Maestria |
| Storage | : Can be kept for 1 year in unopened original container. Protect from freezing and high temperatures. |

PRESTOLITE

Solventborne exterior PLIOLITE[®] based paint



SURFACE PREPARATION

As stated by DTU 59.1, all surfaces must be clean, dry and free of dirt.

Old glossy painted surfaces must be previously sanded or washed with an appropriate cleaner and then rinsed with water.

In the presence of contaminants such as mildew, molds or bacteria, apply an anti-fungal treatment named IKAR AM.

If required an high-pressure cleaning must be carried out, followed by the application of an anti-fungal treatment named IKAR AM.

Do not apply on wood and metal.

These recommendations do not override a specific description of the substrate.

APPLICATION

| | |
|-------------------------------|---|
| Application conditions | : DTU 59.1 |
| Application equipment | : Brush, Facade roller. Airless spray-gun. |
| Clean-up solvent | : White spirit |
| Thinner | : White spirit |
| Dilution | : Brush (0 to 3 %), Facade roller (0 to 3 %). Airless spray-gun (0 to 3 %). |

SYSTEM RECOMMENDATIONS

| Substrate | Primer coat | Top coat |
|---|----------------------------|----------------------------------|
| concrete, cement, hydraulic binder-based coating, previously painted surfaces in good condition | Apply 1 coat of PRESTOLITE | Apply 1 or 2 coats of PRESTOLITE |

CONTAINER SIZE

2.5L - 15L

SAFETY MEASURES

Refer to the Safety Data Sheet