

PRIMAIRE TOLEDO

Primer coating for concrete surfaces coated with TOLEDO systems and cold plastic coatings



Classement AFNOR NFT 36 005 Famille IV Classe 4a

DESCRIPTION

Primer coating for concrete before the application of TOLEDO system or two-component methacrylic-based, colourless and solvent free coatings.

DESTINATION

Primer coating for concrete which must be coated over with a two component methacrylic-based as :- public area- parking lots

FONCTIONAL LIFESPAN

Dose : 400 g/m², depending on the sand depth of the surface.
Drying : 1 hour at 20°C.

PROPERTIES

PRIMAIRE TOLEDO :- prevents absorbance differences,- provides cohesion to the concrete,- in-depth plugging of concrete porosity,- is compatible with all two-component methacrylic-based cold plastic of the range BANDAX ENDUIT TEINTES, TOLEDO TEINTES, AXION OSLO, etc...- enables consistent drying of the finish coating

TECHNICAL FEATURES

Density : 1.00 +/- 0.05 kg/L
Storage : 6 months in its unaltered and sealed original container
Colours : Colourless
Paint thinner : Thinner 258
Clean-up solvent : Thinner EST
Pot life (at 20°C) : 5 min at 20°C.

PRIMAIRE TOLEDO

Primer coating for concrete surfaces coated with TOLEDO systems and cold plastic coatings

APPLICATION

SURFACE PREPARATION

CONCRETE

In compliance with recommendation set forth in DTU 59-3 concerning the preparation and quality of flooring before painting operations: dry surface, clean, free from any form of pollutant, no rising damp and showing sufficient roughness to enable the coating to adhere. The concrete surface must be at least three weeks old prior to application.

CONDITION OF APPLICATION

Surface temperature: Between 5°C and 40°C and at least 3°C higher than the dew point in order to eliminate any risk of condensation. Atmospheric conditions: The temperature must be between 10°C and 40°C. The humidity must be between 0% and 85%.

EQUIPMENT AND DILUTION FOR APPLICATION

Squeegee

Application with a rubber scraper.

Roller

roller 10-12 mm

PRODUCT PREPARATION

PRIMAIRE TOLEDO

PRIMAIRE TOLEDO is a two-component primer. PRIMAIRE TOLEDO should therefore be thoroughly mixed with the content of the two powder bags of hardener.

CLEANING

Cleaning equipment with EST diluting agent.

PACKAGING

5kg kit: base coat + 2 powder bags of hardener.